

**AMENDMENTS TO THE CLAIMS**

**1. (Canceled)**

**2. (Currently amended)** The multilayer hollow container according to ~~Claim 1~~ Claim 3, wherein the co-laminated resin has a glass transition temperature of at most 70 °C.

**3. (Currently amended)** A gas-barrier multilayer hollow container having a co-stretched multilayer wall structure comprising:

a single layer of a polyglycolic acid resin comprising at least 60 wt.% of a recurring unit represented by formula (1),  $(O-CH_2-CO)$  (1), and

a layer of co-laminated resin comprising an aromatic polyester resin or an aliphatic polyester resin other than polyglycolic acid resin laminated on at least one surface of the polyglycolic acid resin layer,

wherein the multilayer wall structure has been cooled once, re-heated and then co-stretched to satisfy formula (2),  $(T \times w/v \leq 0.8 \times 10^{-3})$ , (2), wherein T represents an oxygen gas permeability (ml/container/day/atm), v represents a volume (ml) of the container of at most 700 ml, and w represents a content (wt.%) of the polyglycolic acid resin of 1 - 10 wt.% with respect to a whole weight of the container.

**4. (Currently amended)** The multilayer hollow container according to ~~Claim 1~~ Claim 3, ~~further~~ comprising a laminate of the polyglycolic acid resin and an aromatic polyester resin.

**5. (Currently amended)** The multilayer hollow container according to ~~Claim 1~~ Claim 3, wherein layers of one or both of the aromatic and the aliphatic polyester resin are laminated on both surfaces of and co-stretched with the polyglycolic acid resin layer.

**6. (Previously presented)** The multilayer hollow container according to Claim 5, wherein layers of the aromatic polyester resin are laminated on both surfaces of the polyglycolic acid resin layer.

**7. (Previously presented)** The multilayer hollow container according to Claim 4, wherein the co-laminated resin comprises a recycled resin.

**8. (Previously presented)** The multilayer hollow container according to Claim 7, wherein the recycled resin contains at most 10 wt.% of the polyglycolic acid resin.

**9. (Canceled)**

**10. (Withdrawn)** A process for producing a gas-barrier multilayer hollow container, comprising the steps of: heat-forming a hollow laminate reform having a layer structure including a layer of a polyglycolic acid resin comprising at least 60 wt.% of recurring unit represented by a formula of  $-(O-CH_2-CO)-\cdots(1)$ , and a layer of co-laminated resin comprising an aromatic polyester resin or an aliphatic polyester resin other than polyglycolic acid resin and having a glass-transition point of at least 70 °C laminated on at least one surface of the polyglycolic acid resin layer; cooling the preform; re-heating the preform; and co-stretching the preform.

**11. (Withdrawn)** A production process according to Claim 10, wherein the hollow laminate preform is formed by co-injection.

**12. (Withdrawn)** A production process according to Claim 10, wherein the laminate preform after heating is re-heated to a temperature of at most 90 °C by heating it for 30 - 110 sec. by an infrared heater.

**13. (Withdrawn)** A production process according to Claim 10, wherein the re-heated laminate preform is set in a mold and subjected to blow co-stretching at ratios of longitudinally 1.5 - 4.0 times and transversely 3.0 - 9.0 times.

**14. (Withdrawn)** A production process according to Claim 10, wherein a container after the co-stretching is heat-set by holding it in a heated mold at 70 - 160 °C for 1 - 10 sec.

**15-16. (Canceled)**

**17. (Previously Presented)** The multilayer hollow container according to Claim 3, wherein the polyglycolic acid resin has the following thermal properties:

- a T<sub>g</sub> (glass transition temperature) of 30 - 55 °C,
- a T<sub>c1</sub> (crystallization temperature on temperature increase) of 60 - 135 °C,
- a T<sub>c2</sub> (crystallization temperature on temperature decrease) of 140 - 200 °C, and
- a T<sub>m</sub> (melting point) of 150 - 230 °C.